

POLYPROPYLENE

P6G2Z-090

DESCRIPTION: Impact Copolymer

FEATURES: Excellent impact strength and weldability. Product does not contain animal derived components.

APPLICATIONS: Injection molding and thermoforming: Automotive coolant bottles

PROPERTY	NOMINAL VALUE	SI UNIT	NOMINAL VALUE	ENGLISH UNIT	ASTM TEST METHOD
Melt Flow Rate	1.3	g/10 min.			D 1238
Density	0.90	g/cm ³			D 1505
Tensile Yield Strength	24	MPa	3500	psi	D 638
Ultimate Elongation	>700	%	>700	%	
Modulus	1170	MPa	170	kpsi	
Flexural Modulus	1100	MPa	160	kpsi	D 790
Deflection Temperature @ 66 psi	85	°C	185	°F	D 648
Rockwell Hardness			75	R	D 785
Notched Izod @ 23°C	NB	J/m	NB	ft-lb/in	D 256
Gardner Impact @ -18°C	>36	J	>300	in-lb	D 5420

Jan-10



Regulatory

FDA regulation 21 CFR 177.1520 (c) 3.1
UL Certified 94HB

AUTOMOTIVE APPROVALS

Ford: ESA-M4D472-A, ESB-M4D308-A

118 Huntsman Way, Longview, TX 75602 · Tel: 1-800-985-7303

The data and information represented herein refer to typical values obtained in our laboratories by the methods or apparatuses indicated, and should be so considered. Since processing variables are a major factor in product performance, this information should serve only as a guide. Since customers' testing conditions are outside our control, the reproducibility of our data in a customer's testing facility is not guaranteed. Customer should confirm results under its testing conditions. There is no implied warranty of merchantability or fitness for a particular purpose. Establishing satisfactory performance of the product for the intended application is the customer's sole responsibility. No warranty is given concerning the existence or non-existence of any patents claiming any pertinent subject matter presented herein. The Company assumes no obligation, express or implied, or liability for use of or reliance on the information and data presented. FHR disclaims all product warranties expressed or implied, including warranties of fitness for particular purpose or of merchantability. Further, this product is not intended for use in the manufacture of any form of implanted medical or surgical device.