



## Flint Hills Resources Expandable Polystyrene Grade 54

### I. GENERAL DESCRIPTION

Grade 54 expandable polystyrene is a modified grade resin used for block and shape molding operations, designed for use in a wide range of engineered building applications. It is available in a variety of bead sizes and blowing agent (VOC) content. This product contains a flame retardant and the molded expanded polystyrene has been tested to ASTM C578 standards and classified by Underwriters Laboratories, Inc. for ASTM E 84 and UL-94 properties and by Underwriters Laboratories of Canada for CAN/ULC - S102.2-M88 properties. Within the parameters of the reported test data, expanded polystyrene manufactured from Flint Hills Resources Modified Grade 54 expandable polystyrene complies with the building codes of the United States and Canada, as well as many industrial, military, and federal specifications.

### II. PROPERTIES OF GRADE 54 EXPANDABLE POLYSTYRENE

Type	Bead Size	Typical* Unexpanded Particle Size, (mm)	% Blowing Agent Content	Recommended Density Range** (lbs./ft <sup>3</sup> )	ASTM C- 578 Type	Method of Processing Benefits
I3354	A	1.100 –1.700	3.50 ± 0.30 Ultra low	1.3-2.0	I, VIII, II, XIV, XV	Block Grade Fast cycles at low densities short prepuff age Accepts regrind smooth wire cut surface
5354	B	0.700 –1.400	3.50 ± 0.30 Ultra low	0.90 – 1.25	I, VIII, II, IX	Block grade smooth wire cut surface
S5354	B	0.700-1.400	3.50 ± 0.30 Ultra low	1.25-2.0	I,VIII,II,IX	Shape/Block grade Fast mold cycles at High densities
I5354	B	0.700-1.400	3.50 ± 0.30 Ultra low	1.5-3.0	I,VIII,II,IX,XIV, XV	Shape / Block grade Very fast cycling Smooth wire cut surface
S7354	C	0.400 – 0.800	3.50 ± 0.30 Ultra low	1.15 – 2.00	VIII, II, IX	Shape grade Very fast cycles, excellent part appearance



## Flint Hills Resources Expandable Polystyrene Grade 54

Type	Bead Size	Typical* Unexpanded Particle Size, (mm)	% Blowing Agent Content	Recommended Density Range** (lbs./ft <sup>3</sup> )	ASTM C- 578 Type	Method of Processing Benefits
3454	A	1.100 – 1.700	4.7 ± 0.4 Low	0.90 – 1.25	I, VIII	Block grade Low density accepts regrind
S3454	A	1.100-1.700	4.7 ± 0.4 Low	0.90-1.25	I,VIII	Block fast cycling short prepuff age accepts regrind
5454	B	0.700 – 1.400	4.8 ± 0.3 Low	0.90 – 1.25/	I, VIII, II	Block grade Low density
S5454	B	0.700 – 1.400	4.8 ± 0.3 Low	0.90 – 2.00	VIII, II, IX	Block Grade fast cycling short prepuff age Low – Medium density.
S7454	C	0.400 – 0.800	4.8 ± 0.3 Low	1.25 – 2.50	II, IX, XIV	Block / Shape grade Medium – High density smooth wire cut surface fast Block cycles.
I7454	C	0.400 – 0.800	4.8 ± 0.3 Low	1.15 – 2.50	VIII,II, IX, XIV	Shape grade Medium – High density fast cycles

\*Typical indicates at least 95% of product falls within the given particle size range

\*\*Low density on low pentane products attainable with batch or double pass pre-expansion.



## Flint Hills Resources Expandable Polystyrene Grade 54

Type	Bead Size	Typical* Unexpanded Particle Size, (mm)	% Blowing Agent Content	Recommended Density Range** (lbs./ft <sup>3</sup> )	ASTM C- 578 Type	Method of Processing Benefits
3654	A	1.100 – 1.700	6.5 ± 0.4 Standard	0.90 – 1.25	I, VIII	Block grade low density accepts regrind
5654	B	0.700 – 1.400	6.6 ± 0.4 Standard	0.90 – 1.25	I, VIII	Block grade Low densities Good wire cut surface
S5654	B	0.700- 1.400	6.6 ± 0.4 Standard	0.90-1.25	I,VIII	Block / Shape grade. Fast cycling short prepuff age time.
7654	C	0.400 –0.800	6.4 ± 0.4 Standard	0.90 – 1.50	I, VIII, II	Block grade Fast mold cycles and smooth wire cut surface fabrication
S7654	C	0.400-0.800	6.4 ± 0.4 Standard	0.90-1.50	I,VIII,II	Shape molding fast cycling in the mold.

\*Typical indicates at least 95% of product falls within the given particle size range

\*\*Low density on low pentane products attainable with batch or double pass pre-expansion.



## Flint Hills Resources Expandable Polystyrene Grade 54

---

### III. APPLICATIONS

Grade 54 modified expandable polystyrene resins have gained broad acceptance in the production of consistent, high quality molded products, requiring assembly fire ratings or code approvals. Grade 54 resins have been used in a wide range of engineered building applications including but not limited to Geofoam, Insulated Concrete Forms, Structural Insulated Panels, Roofing, Exterior Insulated Finishing Systems, Slope Stabilization, Highway Embankments and Shallow Foundation Frost protection. To help assure that Flint Hills Resources products are not misapplied, or used in any manner which they may not have been intended or tested, we suggest a review of proposed applications with Flint Hills Resources personnel to assist in dealing with safety considerations. Your Flint Hills Resources Sales Representative can arrange for the proper contact with our Technical Staff for such review.

### IV. SHIPPING AND HANDLING PRECAUTIONS

Expandable polystyrene contains a flammable blowing agent and is consequently regulated by the United States Department of Transportation as a CLASS 9-MISCELLANEOUS MATERIAL. These products are shipped in regulation UN 2211, 2204 - pound flexible bulk packages. Each container is lined with a hydrocarbon barrier liner to decrease the emissions of volatiles. **For further information, please refer to Technical Bulletin TEC-I-002, "Recommended Safety, Health and Environmental Guidelines" and to the Flint Hills Resources Material Safety Data Sheet for product code "Grade 54" name "Expandable Polystyrene (EPS),"** a copy of which is provided with the first shipment or upon request. Printed, Fax, or Electronic File copies of individual MSDS may be requested by contacting our Customer Service representatives, Mon – Fri 8:00 AM to 5:00 PM EST, at 1-800-972-1010 or by going to our website, [www.fhr.com](http://www.fhr.com).

### V. EXPANDABLE POLYSTYRENE MANUFACTURING LOCATIONS

Peru, Illinois

The information contained herein is provided for general purposes only. By providing the information contained herein, Flint Hills Resources, LP makes no guarantee or warranty, and does not assume any liability with respect to the accuracy or completeness of such information, or the product results in any specific instance and hereby expressly disclaims any implied warranties of merchantability or fitness for a particular purpose, or any other warranties or representations whatsoever, expressed or implied. Nothing contained herein shall be construed as a license to use the Flint Hills Resources, LP in any manner that would infringe any patent.